

## AB-138

### FEATURES

- Superior tensile strength
- Tear and abrasion resistant
- Made with FDA compliant ingredients
- Easier buffing
- ASTM Grade

GRADE	Industrial
FINISH	Smooth
POWDER	Yes
TRIMMED	Yes
COLOR	Beige

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M <sup>2</sup> )	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
128-04-362	1/16 (1.59)	36 (914.4)	300 (27.87)	100 (30.48)	108 (49)
128-04-482	1/16 (1.59)	48 (1219.2)	400 (37.16)	100 (30.48)	144 (65.3)
128-06-362 <sup>1</sup>	3/32 (2.38)	36 (914.4)	225 (20.9)	75 (22.85)	129 (58.5)
128-06-482 <sup>1</sup>	3/32 (2.38)	48 (1219.2)	300 (27.87)	75 (22.85)	172 (78)
128-08-362	1/8 (3.7)	36 (914.4)	150 (13.93)	50 (15.24)	108 (49)
128-08-482	1/8 (3.7)	48 (1219.2)	200 (18.58)	50 (15.24)	144 (65.3)
128-12-362	3/16 (4.76)	36 (914.4)	120 (11.15)	40 (12.19)	140 (63.5)
128-12-482	3/16 (4.76)	48 (1219.2)	160 (14.86)	40 (12.19)	186 (84.4)
128-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	173 (78.5)
128-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	231 (104.8)
128-24-362 <sup>1</sup>	3/8 (9.52)	36 (914.4)	90 (8.36)	30 (9.14)	195 (88.5)
128-24-482	3/8 (9.52)	48 (1219.2)	120 (11.15)	30 (9.14)	260 (117.9)
128-32-362	1/2 (12.70)	36 (914.4)	150 (13.93)	50 (15.24)	439 (199.1)
128-32-482	1/2 (12.70)	48 (1219.2)	200 (18.58)	50 (15.24)	586 (265.8)
128-40-362 <sup>1</sup>	5/8 (15.90)	36 (914.4)	90 (8.36)	30 (9.14)	328 (148.8)
128-40-482 <sup>1</sup>	5/8 (15.90)	48 (1219.2)	120 (11.15)	30 (9.14)	438 (198.7)
128-48-362	3/4 (19.00)	36 (914.4)	90 (8.36)	30 (9.14)	389 (176.5)
128-48-482	3/4 (19.00)	48 (1219.2)	120 (11.15)	30 (9.14)	519 (235.4)
128-64-362	1 (25.40)	36 (914.4)	90 (8.36)	30 (9.14)	525 (238.1)

<sup>1</sup> Made to order



# TECHNICAL SPECIFICATIONS AB-138

SPECIFICATION ASTM D2000 : 2AA420A13F17  
POLYMER : Natural Rubber Blend (Beige)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.14
D2240	HARDNESS (Shore A)	40
D412	TENSILE (psi)	2000 min.
	ULTIMATE ELONGATION (%)	400 min.
D2137	COLD TEMPERATURE	-40°C min.
D395B	COMPRESSION SET	22 hrs @ 70°C 50% max.
D573	HEAT AGING	70 hrs @ 70°C Changed Hardness: 15 points max. Tensile: +/- 30% max. Elongation: -50% max.
TEMPERATURE RANGE (general guideline)		-20° to 180° F (-29° to 82° C)
Maximum pieces per roll : 2		
Minimum piece length : 10'		
Width tolerance: -0 / +1"		
Length tolerance: 1/16" to 1/2" +/- 10% (5/8" to 1" + 10%, Min. 10')		
Material is within RMA commercial gauge tolerances.		
Made with FDA compliant ingredients (FDA 21 CFR 177.2600 and 182.8991 - rubber articles intended for repeated food exposure)		

Please ensure the product meets your application specification prior to order placement.  
Specifications are subject to change without notice. The website version prevails.